



ISO	Property Description	Data
20795-1	Flexural Strength	> 85 MPa
	Flexural Modulus	> 2000 MPa
D638M	Elongation at Break	< 5.0%
178	Hardness (Shore D)	> 80